

Trademark and type of board: TABLEX, Hardboard (HB)

Mix of species: > 90% Eucalyptus Spp; the rest other hardwood: quercus robur, quercus pyrenaica, castanea sativa, Betula spp, Fraxinus spp, Alnus glutinosa, Salix spp, acacia dealbata, acacia melanoxylon.

Wood origin: Spain, more than 99% from Galicia.

Description

SUPERLAC is a high-density wood fibreboard with a smooth side and a rough side for non-structural use in general interior applications. Particularly suitable for lacquering; the smooth side offers an even, low porosity surface, providing a surface quality in finishes with paint.

The Superlac board is a very versatile material, suitable for designers and industrialists as a decorative backing for a wide range of interior applications.

Specifications

Properties	Reference Test	Units	Thickness (mm)		
			2,0 - 2,5 - 3,0 - 3,2	4,8 - 5,4	6,0 - 6,4
Thickness	EN 324-1	mm	± 0,3	± 0,5	± 0,7
Length and Width	EN 324-1	mm/m	± 2 (up to 5mm)	± 2 (up to 5mm)	± 2 (up to 5mm)
Squareness	EN 324-2	mm/m	≤ 2	≤ 2	≤ 2
Density	EN 323	Kg/m ³	≥ 900	≥ 900	≥ 900
Moisture Content	EN 322	%	4 a 9	4 a 9	4 a 9
Flexural Strength	EN 310	N/mm ²	≥ 30	≥ 30	≥ 30
Tensile Strength	EN 319	N/mm ²	≥ 0,70	≥ 0,70	≥ 0,70
Swelling in Thickness 24h	EN 317	%	≤ 37	≤ 30	≤ 25

Values based on Standard **UNE-EN 622-2** and **EN 13986**.


Note: The dimensional characteristics may change according to the time and storage conditions.

Formaldehyde content

Wood-only board recommended for use in a dry environments. No added artificial resins are used in the manufacture of the **Superlac** board, as the fibres are bonded with lignin, a natural wood adhesive, making it a **single-component** material, and therefore easily recoverable and durable. For this reason, the formaldehyde emission levels of these boards are similar to those of natural wood.

Handling and storage

Avoid inhaling the wood dust generated during its handling and processing. Use appropriate PPE according to current legislation. The boards should be stored on a flat surface, avoiding direct contact with the ground and water, maintaining the distances between battens supplied in the packaging to avoid bending and deformations. Sudden changes in these conditions may affect the properties of the board.



Product available with EC declaration in accordance with European Standard EN 13986 and manufactured in EN ISO 9001, ISO 14001, ISO 45001 and ISO 50001 certified facilities. PEFC and FSC certificates upon request.